

G-PLY™ FX TL845 T3

N° FICHE TECHNIQUE : RPY 794 Data Sheet Number / Technische Daten Nummer	Date d'émission Issue date/Datumssendung	27.11.20
	Indice de révision Inspection Index Überhebungszahl	01 du 13.01.21

Poids au m² sans intercalaire/Weight without intercalary 864 g/m² ± 5 %

Epaisseur intercalaire (valeur indicative)/Intercalary thickness (indicative value) 20 to 50 µ

COMPOSANTS/Components/Bauelemente

CHAINE (0°)/Warp/Kette Matière/Substance/Stoff Poids/Weight/Gewicht	1200 Tex VERRE/Glass	300 g/m ²
DIAGONALE + 45° Matière/Substance/Stoff Poids/Weight/Gewicht	600 Tex VERRE/Glass	272 g/m ²
DIAGONALE – 45° Matière/Substance/Stoff Poids/Weight/Gewicht	600 Tex VERRE/Glass	272 g/m ²
LIAGE/Binding/Binder Matière/Substance/Stoff Poids/Weight/Gewicht	TRICOT POLYESTER/Polyester	10 g/m ²
ADHESIF/Adhésive Poids/Weight/Gewicht	COMPATIBLE UP /VINYLESTER	10 g/m ²

OBSERVATIONS

Observations/Bemerkungen

"RENFORT AUTOCOLLANT" - TEMPERATURE MINIMALE D'UTILISATION : 20° C

Autoadhesive reinforcement – We recommend to use it at temperature over 20°C

PRODUCT UNDER DEVELOPMENT/PRODUIT EN DEVELOPPEMENT

A utiliser au plus tard 1 an après la date de fabrication – Température maximum de stockage 30°C – Stocker dans un endroit sec

To be used within one year after the date of manufacture – Maximum storage temperature 30°C – Store in a dry place

CHOMARAT Textiles Industries

39, avenue de Chabannes

07160 LE CHEYLARD – France

tél. +33 (0)4 75 29 81 00

fax +33 (0)4 75 29 20 12

info@chomarar.com – www.chomarar.com

siret : 50160786500018 – TVA FR42501607865

Important: All properties are average values given for indication. Values are not intended for use as a specification. : Information given in this document is based on the present knowledge of the technical properties of our product.

All information is believed to be accurate but is given without acceptance of liability. Users should make their own assessment of the suitability of any product for the purposes required. Information contained in the present document refers to the product specifically indicated and cannot be valid in combination with other products.

All sales are subject to our standard terms of sale which include limitations on liability and other important terms.

Important: Toutes les propriétés sont des valeurs moyennes données à titre indicatif et ne peuvent être utilisées comme spécifications. Les informations données dans cette fiche technique sont basées sur l'état de nos connaissances actuelles Toutes ces informations sont supposées correctes mais données sans acceptation de responsabilité. Les utilisateurs doivent évaluer le produit en fonction de l'utilisation qui doit en être faite.

Les informations contenues dans le présent document se rapportent au produit spécifiquement désigné et ne peuvent être valables en combinaison avec d'autres produits. Toutes les ventes sont soumises à nos conditions générales de vente.